

TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. § 371		Attorney Docket No. V20.12-0001 U.S. Application No. 09/913673
INTERNATIONAL APPLICATION PCT/AU00/00117	INTERNATIONAL FILING DATE 16 February 2000 (16.02.00)	PRIORITY DATE CLAIMED 17 February 1999 (17.02.99)
TITLE OF INVENTION ERASABLE/REWRITABLE OPTICAL DATA STORAGE WITH PHOTOREFRACTIVE POLYMERS		
APPLICANT(S) FOR DO/EO/US GU, Min et al.		
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:		
<ol style="list-style-type: none"> 1. <input checked="" type="checkbox"/> This is a FIRST submission of items concerning a filing under 35 U.S.C. 371. 2. <input type="checkbox"/> This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371. 3. <input checked="" type="checkbox"/> This is an express request to begin national examination procedures (35 U.S.C. 371(f) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(I). 4. <input checked="" type="checkbox"/> A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date. 5. <input checked="" type="checkbox"/> A copy of the International Application as filed (35 U.S.C. 371(c)(2)) <ol style="list-style-type: none"> a. <input checked="" type="checkbox"/> is transmitted herewith (required only if not transmitted by the International Bureau). b. <input type="checkbox"/> has been transmitted by the International Bureau. c. <input type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US). 6. <input type="checkbox"/> A translation of the International Application into English (35 U.S.C. 371(c)(2)). 7. <input checked="" type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)) <ol style="list-style-type: none"> a. <input checked="" type="checkbox"/> are transmitted herewith (required only if not transmitted by the International Bureau) b. <input checked="" type="checkbox"/> have been transmitted by the International Bureau. c. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired. d. <input type="checkbox"/> have not been made and will not be made. 8. <input type="checkbox"/> A translation of the amendment to the claims under PCT Article 19 (35 U.S.C. 372(c)(3)). 9. <input checked="" type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)). 10. <input type="checkbox"/> A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 37(c)(5)). 		
Items 11. to 16. below concern document(s) or information included:		
<ol style="list-style-type: none"> 11. <input checked="" type="checkbox"/> An Information Disclosure Statement under 37 CFR 1.97 and .198. 12. <input type="checkbox"/> An assignment document for recording. A separate cover sheet in compliance with 37 C.F.R. 3.28 and 3.31 is included. 13. <input checked="" type="checkbox"/> A FIRST preliminary amendment <input type="checkbox"/> A SECOND or SUBSEQUENT preliminary amendment. 14. <input type="checkbox"/> A substitute specification. 15. <input type="checkbox"/> A change of power of attorney and/or address letter. 16. <input checked="" type="checkbox"/> Other items or information: <ol style="list-style-type: none"> A. International Preliminary Examination Report B. Written Opinion C. Response to Written Opinion D. Response to Supplementary International Search Report E. Six (6) sheets of drawings F. Abstract typed on a separate page 		

U.S. APPLICATION NO. 09/913673		INTERNATIONAL APPLICATION NO. PCT/AU00/00117		ATTORNEY'S DOCKET NUMBER V20.12-0001	
--	--	---	--	---	--


17. <input checked="" type="checkbox"/> The following fees are submitted: BASIC NATIONAL FEE (37 CFR 1.492(A)(1)-(5)): Search Report has been prepared by the EPO or JPO..... \$860.00 International preliminary examination fee paid to USPTO (37 CFR 1.482) \$690.00 No international preliminary examination fee paid to USPTO (37 CFR 1.482) but international search fee paid to USPTO (37 CFR 1.445(a)(2))..... \$710.00 Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO..... \$1,000.00 International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(2)-(4)..... \$100.00				CALCULATIONS PTO USE ONLY	
ENTER APPROPRIATE BASIC FEE AMOUNT =				\$860	
Surcharge of \$130.00 for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(e)).				\$0	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total claims	45 - 20 =	25	X \$18	\$450	
Independent claims	6 - 3 =	3	X \$80	\$240	
MULTIPLE DEPENDENT CLAIM (S) (if applicable)			+ \$270.00	\$0	
TOTAL OF ABOVE CALCULATIONS =				\$1,550	
Reduction by 1/2 for filing by small entity. It is asserted by the undersigned, the applicant is entitled to small entity status.				\$775 -	
SUBTOTAL =				\$775	
Processing fee of \$130.00 for furnishing the English translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(f))				\$0	
TOTAL NATIONAL FEE =				\$775	
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property.				\$0 +	
TOTAL FEES ENCLOSED =				\$775	
				Amount to be:	
				refunded \$	
				charged \$	

- a. ☒ A Credit Card Payment Form - PTO 2038 in the amount of \$775 to cover the above fees is enclosed.
- b. ☐ Please charge my Deposit Account No. **23-1123** in the amount of \$ to cover the above fees.
A duplicate copy of this sheet is enclosed.
- c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment,
to Deposit Account No. **23-1123**. A duplicate copy of this sheet is enclosed.

NOTE: Where an appropriate time limit under 37 C.F.R. 1.494 or 1.495 has not been met, a petition to revive (1.37(a) or (b)) must be filed and granted to restore the application to pending status.

Send all correspondence to:

Nickolas E. Westman
WESTMAN, CHAMPLIN & KELLY, P.A.
Suite 1600 - International Centre
900 Second Avenue South
Minneapolis, MN 55402-3319


 Signature
 Nickolas E. Westman
 Reg. No. 20,147

Express Mail No. EL844348900US

UNITED STATES RECEIVING OFFICE (RO/US)

Re	International Appln. No. PCT/AU00/00117
Applicant	GU, Min et al.
International Filing Date	16 February 2000 (16.02.00)
Title of Invention	ERASABLE/REWRITABLE OPTICAL DATA STORAGE WITH PHOTOREFRACTIVE POLYMERS
Agent's File	V20.12-0001

Letter

EL844348900US


August 17, 2001

"Express Mail" Mailing Number

Date of Deposit

The following are being deposited with the United States Postal Service "Express Mail Post Office to Addressee" addressed to Box PCT, Assistant Commissioner for Patents, Washington, D.C. 20231:

1. Credit Card Payment Form - PTO 2038 for \$775 Filing Fee
2. Transmittal Letter (completed Form No. PTO-1390)
3. Paper entitled "NATIONAL FILING IN U.S. RECEIVING OFFICE"
4. Preliminary Amendment
5. Copy of front page only of International Publication No. WO 00/49465 (PCT/AU00/00117)
6. Copy of specification and drawings as originally filed
7. Combined Declaration and Power of Attorney
8. International Preliminary Examination Report
9. Two International Search Reports issued by EPO
10. Information Disclosure Statement with copies of cited references
11. Written Opinion
12. Response to Written Opinion
13. Response to Supplementary International Search Report
14. Abstract typed on a separate page


Nickolas E. Westman, Reg. No. 20,147
WESTMAN, CHAMPLIN & KELLY, P.A.
Suite 1600 - International Centre
900 Second Avenue South
Minneapolis, Minnesota 55402-3319
Telephone : 612/334-3222
Telefacsimile: 612/334-3312

NEW:daw

PTO/PCT Rec'd 25 OCT 2001


UNITED STATES RECEIVING OFFICE (RO/US)

Re	International Appln. No. PCT/AU00/00117
Applicant	GU, Min et al.
International Filing Date	16 February 2000 (16.02.0000)
U.S. Applic. No.	09/913,673
U.S. Filing Date	August 17, 2001
Title of Invention	ERASABLE/REWRITABLE OPTICAL DATA STORAGE WITH PHOTOREFRACTIVE POLYMERS
Agent's File	V20.12-0001

SECOND PRELIMINARY AMENDMENT

Box PCT
Assistant Commissioner for Patents
Washington, D.C. 20231

I HEREBY CERTIFY THAT THIS PAPER IS BEING
SENT BY U.S. MAIL, FIRST CLASS, TO THE
ASSISTANT COMMISSIONER FOR PATENTS,
WASHINGTON, D.C. 20231, THIS

25 DAY OF October 2001.

PATENT ATTORNEY

Sir:

Please enter the following Second Preliminary Amendment
in the above-identified application.

IN THE SPECIFICATION


Immediately after the title on page 1 please add the
following paragraph:

This application is a national stage filing under 35
U.S.C. §371 and priority is hereby claimed on International
Application No. PCT/AU00/00117, Filed 16 February 2000, which
International Application was published in English as No. WO
00/49465.

REMARKS

Entry of the above Second Preliminary Amendment for claiming priority is requested.

Respectfully submitted,



Nickolas E. Westman, Reg. No. 20,147

WESTMAN, CHAMPLIN & KELLY, P.A.

Suite 1600 - International Centre

900 Second Avenue South

Minneapolis, Minnesota 55402-3319

Telephone : 612/334-3222

Telefacsimile: 612/334-3312

BDK/djb

MARKED-UP VERSION OF REPLACEMENT PARAGRAPHS

Immediately after the title on page 1 please add the following paragraph:

This application is a national stage filing under 35 U.S.C. §371 and priority is hereby claimed on International Application No. PCT/AU00/00117, Filed 16 February 2000, which International Application was published in English as No. WO 00/49465.

DISPATCHED 17 AUG 2001

Express Mail No. EL844348900US

UNITED STATES RECEIVING OFFICE (RO/US)

Re	International Appln. No. PCT/GB97/01984
Applicant	GU, Min et al.
International Filing Date	16 February 2000 (16.02.0000)
Title of Invention	ERASABLE/REWRITABLE OPTICAL DATA STORAGE WITH PHOTOREFRACTIVE POLYMERS
Agent's File	V20.12-0001

PRELIMINARY AMENDMENT AND
REQUEST NOT TO ENTER ANY AMENDMENTS
UNDER ARTICLE 34 OF THE PCT

Box PCT
Assistant Commissioner for Patents
Washington, D.C. 20231

Sir:

Prior to calculation of the filing fee for this application, please enter the following Preliminary Amendment:

If any amendments have been filed under Article 34 of the Patent Cooperation Treaty, applicants request that these amendments not be entered as a part of this national filing.

Entry of the amended claims filed under Article 19 is believed to have occurred.

The following Amendments apply to the claims as filed under Article 19.

IN THE CLAIMS

Please amend claims 1-4, 6-26, 28-30, 32, 34, 36-43 as follows:

1. (Amended) A method of writing and erasing optical data comprising;

focusing light on a photorefractive polymeric material to cause two-photon excitation of the material at the focal point thereby modulating the refractive index at the focal point to record data; and

illuminating the material with radiation to erase the

recorded data.

2. (Amended) A method of writing and re-writing optical data in a photorefractive polymeric material comprising:

focusing light on the photorefractive polymeric material to cause two-photon excitation of the material at the focal point of the beam thereby modulating the refractive index at the focal point to write data;

illuminating the material with radiation to erase the recorded data;

focusing light on the photorefractive polymeric material to cause two-photon excitation of the material at the focal point thereby modulating the refractive index at the focal point to re-write data in the photorefractive polymeric material.

3. (Amended) A method according to claim 1 wherein the modulation of the refractive index caused by the two-photon excitation is a refractive index inhomogeneity resulting from a non-uniform space-charge distribution within the region of excitation within the photorefractive polymeric material.

4. (Amended) A method according to any one of claim 1 wherein the photorefractive material is illuminated with electro-magnetic radiation having a wavelength in the ultraviolet (UV) or visible spectrum to produce a redistribution of the spacial distribution of the electric charges forming bits of the data to erase the recorded data.

6. (Amended) A method according to claim 4 wherein the maximum of the absorption band of the photorefractive polymeric material falls substantially within the range from about 380 nm to about 600 nm.

7. (Amended) A method according to claim 4 wherein the

photorefractive polymeric material is such that it absorbs substantially no radiation above a wavelength of about 630 nm.

8. (Amended) A method according to claim 1 wherein the data recorded in the photorefractive polymeric material is read by illuminating the photorefractive polymeric material with coherent light of a wavelength falling substantially within the range from about 630 nm to about 1200 nm.

9. (Amended) A method according to claim 1 wherein the light used to record data in the photorefractive material has a wavelength falling substantially within the range from about 750 nm to about 1200 nm to cause two-photon excitation.

10. (Amended) A method according to claim 1 wherein a pulsed laser beam is used to record data in the photorefractive polymeric material.

11. (Amended) A method according to claim 1 wherein a continuous wave laser beam is used to record data in the photorefractive polymeric material.

12. (Amended) A method according to claim 1 wherein polarized coherent light is used to record polarized bits of data in the photorefractive polymeric material.

13. (Amended) A method according to claim 12 wherein different polarization states of the recording beam are used to record multiple bits of data at the same position having different polarization states in the photorefractive polymeric material.

14. (Amended) A method according to claim 12 wherein bits of recorded data are read by using a reading beam having an appropriate polarization state.

15. (Amended) A method according to claim 12 wherein individual bits of data are erasable by changing the polarization state of the individual bits.

16. (Amended) A method according to claim 1 wherein the photorefractive polymeric material includes at least about 25% of a polymer by percentage weight of the total weight of the photorefractive material.

17. (Amended) A method according to claim 1 wherein the photorefractive polymeric material includes a chromophore which provides absorption in the UV to visible region of the electromagnetic spectrum.

18. (Amended) A method according to claim 1 wherein the photorefractive polymeric material includes a photosensitive material which provides absorption in the UV to visible region of the electromagnetic spectrum.

19. (Amended) A method according to claim 1 wherein the photorefractive polymeric material includes a plasticizer to reduce the glass transition temperature of the material.

20. (Amended) A method according to claim 1 wherein the photorefractive material includes at least some of the following materials in quantities falling substantially within the following ranges by percentage of the total weight of the photorefractive material:

- 25% - 99.5% of a polymer;
- 0.5%-60% of a chromophore;
- 0.5%-5% of a photosensitive material; and
- 0% - 40% of a plasticizer.

21. (Amended) A method according to claim 16 wherein the polymer comprises poly (*N*-vinylcarbazole) (PVK).

22. (Amended) A method according to claim 16 wherein the polymer comprises poly (methyl methacrylate) (MMA).

23. (Amended) A method according to claim 17 wherein the chromophore comprises 2, 5- dimethyl - 4 - (p-nitro-phenylazo) anisole (DMNPAA).

24. (Amended) A method according to claim 18 wherein the photosensitive material comprises 2, 4, 7-trinitro-9-fluorenone (TNF).

25. (Amended) A method according to claims 19 wherein the plasticizer comprises *N*-ethylcarbazole (ECZ).

26. (Amended) A photorefractive polymeric optical data storage material for use in a method of erasable/rewritable optical data storage, the photorefractive polymeric material providing absorption in the UV to visible region of the electromagnetic spectrum, wherein the absorption band of the photorefractive material is such as to enable the recording of bits of data by two photon excitation, the reading of the bits of data by a source of coherent light on the edge of or outside the absorption band, and the erasing of the bits of data by illumination with radiation within the absorption band.

28. (Amended) A photorefractive polymeric material according to claim 26 wherein the upper end of the absorption band of the photorefractive polymeric material is about 630 nm.

29. (Amended) A photorefractive polymeric material according to

claim 26 wherein the material includes at least about 25% of a polymer by percentage weight of the total weight of the photorefractive material.

30. (Amended) A photorefractive polymeric material according to claim 26 wherein the material includes a chromophore which provides absorption in the UV to visible region of the electromagnetic spectrum.

32. (Amended) A photorefractive polymeric material according to claim 26 wherein the material includes a photosensitive material which provides absorption in the UV to visible region of the electromagnetic spectrum.

34. (Amended) A photorefractive polymeric material according to claim 26 wherein the material includes a plasticizer to reduce the glass transition temperature of the material.

36. (Amended) A photorefractive optical data storage medium for use in a method of erasable/rewritable optical data storage in which light is focused on the data storage medium to modulate the refractive index at the focal point by two-photon excitation, wherein the medium includes at least some of the following materials in quantities falling substantially within the following ranges by percentage of the total weight of the photorefractive data storage medium:

- 25% - 99.5% of a polymer;
- 0.5% - 60% of a chromophore;
- 0.5% - 5% of a photosensitive material; and
- 0% - 40% of a plasticizer.

37. (Amended) A photorefractive optical data storage medium according to claim 29 wherein the polymer comprises poly (N-vinylcarbazole) (PVK).

38. (Amended) A photorefractive optical data storage medium according to claim 29 wherein the polymer comprises poly (methyl methacrylate) (PMMA).

39. (Amended) A photorefractive optical data storage medium according to claim 30 wherein the chromophore comprises 2,5-dimethyl-4-(p-nitro phenylazo) anisole (DMNPAA).

40. (Amended) A photorefractive optical data storage medium according to claim 32 wherein the photosensitive material comprises 2, 4, 7-trinitro-9-fluorenone (TNF).

41. (Amended) A photorefractive optical data storage medium according to claims 34 wherein the plasticiser comprises N-ethylcarbazole (ECZ).

42. (Amended) A photorefractive optical data storage medium adapted for use in a method of erasable/rewritable optical data storage in which the light is focused on the data storage medium to modulate the refractive index at the focal point by two photon excitation, wherein the medium includes the following materials:

poly(N-vinylcarbazole) (PVK);
2,5, dimethyl-4-(p-nitrophenylazo) anisole (DMNPAA)
2,4,7-trinitro-9-fluorenone (TNF); and
N-ethylcarbazole (ECZ).

43. (Amended) A photorefractive optical data storage medium according to claim 42 wherein the PVK;DMNPAA;TNF and ECZ are present in approximately the following concentrations by percentage weight of the total weight of the photorefractive material 33:50:1:16.


REMARKS

The above amendments are made to eliminate multiple dependent claims.

Also, please do not enter the amended pages submitted under Article 34. This Preliminary Amendment conforms the claims from the Amendments Under Article 19 to conform to the claims considered in the International Preliminary Examination Report.

Entry of the Amendment prior to calculating the filing fee is respectfully requested.

Respectfully submitted,



Nickolas E. Westman, Reg. No. 20,147
WESTMAN, CHAMPLIN & KELLY, P.A.
Suite 1600 - International Centre
900 Second Avenue South
Minneapolis, Minnesota 55402-3319
Telephone : 612/334-3222
Telefacsimile: 612/334-3312

NEW/djb

2025 RELEASE UNDER E.O. 14176

MARKED-UP VERSION OF REPLACEMENT CLAIMS

1. (Amended) A method of writing and erasing optical data comprising;

~~foe~~ussingfocusing light on a photorefractive polymeric material to cause two-photon excitation of the material at the focal point thereby modulating the refractive index at the focal point to record data; and

illuminating the material with radiation to erase the recorded data.

2. (Amended) A method of writing and re-writing optical data in a photorefractive polymeric material comprising:

~~foe~~ussingfocusing light on the photorefractive polymeric material to cause two-photon excitation of the material at the focal point of the beam thereby modulating the refractive index at the focal point to write data;

illuminating the material with radiation to erase the recorded data;

~~foe~~ussingfocusing light on the photorefractive polymeric material to cause two-photon excitation of the material at the focal point thereby modulating the refractive index at the focal point to re-write data in the photorefractive polymeric material.

3. (Amended) A method according to claim 1 ~~or claim 2~~ wherein the modulation of the refractive index caused by the two-photon excitation is a refractive index inhomogeneity resulting from a non-uniform space-charge distribution within the region of excitation within the photorefractive polymeric material.

4. (Amended) A method according to any one of claims 1 ~~to 3~~ wherein the photorefractive material is illuminated with electromagnetic radiation having a wavelength in the ultraviolet (UV) or

visible spectrum to produce a redistribution of the spacial distribution of the electric charges forming bits of the data to erase the recorded data.

6. (Amended) A method according to ~~claim 4 or claim 5~~ wherein the maximum of the absorption band of the photorefractive polymeric material falls substantially within the range from about 380 nm to about 600 nm.

7. (Amended) A method according to ~~any one of claims 4 to 6~~ wherein the photorefractive polymeric material is such that is absorbs substantially no radiation above a wavelength of about 630 nm.

8. (Amended) A method according to ~~any one the preceding claims 1~~ wherein the data recorded in the photorefractive polymeric material is read by illuminating the photorefractive polymeric material with coherent light of a wavelength falling substantially within the range from about 630 nm to about 1200 nm.

9. (Amended) A method according to ~~any one of the preceding claims 1~~ wherein the light used to record data in the photorefractive material has a wavelength falling substantially within the range from about 750 nm to about 1200 nm to cause two-photon excitation.

10. (Amended) A method according to ~~any one of the preceding claims 1~~ wherein a pulsed laser beam is used to record data in the photorefractive polymeric material.

11. (Amended) A method according to ~~any one of claims 1 to 9~~ wherein a continuous wave laser beam is used to record data in the photorefractive polymeric material.

12. (Amended) A method according to ~~any one of the preceding claims 1~~ wherein ~~polarised~~polarized coherent light is used to record ~~polarised~~polarized bits of data in the photorefractive polymeric material.

13. (Amended) A method according to claim 12 wherein different ~~polarisation~~polarization states of the recording beam are used to record multiple bits of data at the same position having different ~~polarisation~~polarization states in the photorefractive polymeric material.

14. (Amended) A method according to claim 12 ~~or claim 13~~ wherein bits of recorded data are read by using a reading beam having an appropriate ~~polarisation~~polarization state.

15. (Amended) A method according to ~~any one of claims 12 to 14~~ wherein individual bits of data are erasable by changing the ~~polarisation~~polarization state of the individual bits.

16. (Amended) A method according to ~~any one of the preceding claims 1~~ wherein the photorefractive polymeric material includes at least about 25% of a polymer by percentage weight of the total weight of the photorefractive material.

17. (Amended) A method according to ~~any one of the preceding claims 1~~ wherein the photorefractive polymeric material includes a chromophore which provides absorption in the UV to visible region of the electromagnetic spectrum.

18. (Amended) A method according to ~~any one of the preceding claims 1~~ wherein the photorefractive polymeric material includes a photosensitive material which provides absorption in the UV to visible region of the electromagnetic spectrum.

19. (Amended) A method according to ~~any one of the preceding claims~~ 1 wherein the photorefractive polymeric material ~~includes~~includes a ~~plasticizer~~plasticizer to reduce the glass transition temperature of the material.

20. (Amended) A method according to ~~any one of the preceding claims~~ 1 wherein the photorefractive material includes at least some of the following materials in quantities falling substantially within the following ranges by percentage of the total weight of the photorefractive material:

- 25% - ~~100~~99.5% of a polymer;
- 0.5%-60% of a chromophore;
- 0.5%-5% of a photosensitive material; and
- 0% - 40% of a ~~plasticizer~~plasticizer.

21. (Amended) A method according to claim 16 ~~or claim 20~~ wherein the polymer comprises poly (*N*-vinylcarbazole) (PVK).

22. (Amended) A method according to claim 16 ~~or claim 20~~ wherein the polymer comprises poly (methyl methacrylate) (MMA).

23. (Amended) A method according to claim 17 ~~or any one of claims 20 to 22~~ wherein the chromophore comprises 2, 5- dimethyl - 4 - (p-nitro-phenylazo) anisole (DMNPAA).

24. (Amended) A method according to claim 18 ~~or any one of claims 20 to 22~~ wherein the photosensitive material comprises 2, 4, 7-trinitro-9-fluorenone (TNF).

25. (Amended) A method according to ~~any one of claims 19 to 24~~ wherein the ~~plasticizer~~plasticizer comprises *N*-ethylcarbazole (ECZ).

26. (Amended) A photorefractive polymeric optical data storage material for use in a method of erasable/rewritable optical data storage, the photorefractive polymeric material providing absorption in the UV to visible region of the electromagnetic spectrum, wherein the absorption band of the photorefractive material is such as to enable the recording of bits of data by two photon ~~exciation~~excitation, the reading of the bits of data by a source of coherent light on the edge of or outside the absorption band, and the erasing of the bits of data by illumination with radiation within the absorption band.

28. (Amended) A photorefractive polymeric material according to claim 26 ~~or claim 27~~ wherein the upper end of the absorption band of the photorefractive polymeric material is about 630 nm.

29. (Amended) A photorefractive polymeric material according to ~~any one of claims 26 to 28~~ wherein the material includes at least about 25% of a polymer by percentage weight of the total weight of the photorefractive material.

30. (Amended) A photorefractive polymeric material according to ~~any one of claims 26 to 29~~ wherein the material includes a chromophore which provides absorption in the UV to visible region of the electromagnetic spectrum.

32. (Amended) A photorefractive polymeric material according to ~~any one of claims 26 to 31~~ wherein the material includes a photosensitive material which provides absorption in the UV to visible region of the electromagnetic spectrum.

34. (Amended) A photorefractive polymeric material according to ~~any one of claims 26 to 33~~ wherein the material includes a ~~plasticiser~~plasticizer to reduce the glass transition temperature

of the material.

36. (Amended) A photorefractive optical data storage medium ~~polymeric material~~ for use in a method of erasable/rewritable optical data storage in which light is ~~focussed~~ focused on the data storage medium to modulate the refractive index at the focal point by two-photon excitation, wherein the ~~material~~ medium includes at least some of the following materials in quantities falling substantially within the following ranges by percentage of the total weight of the photorefractive ~~polymeric material~~ data storage medium:
+

- 25% - ~~100~~ 99.5% of a polymer;
- 0.5% - 60% of a chromophore;
- 0.5% - 5% of a photosensitive material; and
- 0% - 40% of a ~~plasticiser~~ plasticizer.

37. (Amended) A photorefractive optical data storage medium ~~polymeric material~~ according to claim 29 ~~or claim 36~~ wherein the polymer comprises poly (N-vinylcarbazole) (PVK).

38. (Amended) A photorefractive optical data storage medium ~~polymeric material~~ according to claim 29 ~~or claim 36~~ wherein the polymer comprises poly (methyl methacrylate) (PMMA).

39. (Amended) A photorefractive optical data storage medium ~~polymeric material~~ according to ~~any one of claims 30, 31 or 36 to 38~~ wherein the chromophore comprises 2,5-dimethyl-4-(p-nitro phenylazo) anisole (DMNPAA).

40. (Amended) A photorefractive optical data storage medium ~~polymeric material~~ according to ~~any one of claims 32, 34 or 36 to 39~~ wherein the photosensitive material comprises 2, 4, 7-trinitro-9-fluorenone (TNF).

41. (Amended) A photorefractive optical data storage medium~~polymeric material~~ according to ~~any one of claims 34 to 40~~ wherein the plasticiser comprises N-ethylcarbazole (ECZ).

42. (Amended) A photorefractive optical data storage medium adapted for use in ~~polymeric material for use in a~~ method of erasable/rewritable optical data storage in which the light is focused on the data storage medium to modulate the refractive index at the focal point by two photon excitation, wherein the medium includes~~comprising~~ the following materials:

poly(N-vinylcarbazole) (PVK);
2,5, dimethyl-4-(p-nitrophenylazo) anisole (DMNPAA)
2,4,7-trinitro-9-fluorenone (TNF); and
N-ethylcarbazole (ECZ).

43. (Amended) A photorefractive optical data storage medium~~material~~ according to claim 42 wherein the PVK;DMNPAA;TNF and ECZ are present in approximately the following concentrations by percentage weight of the total weight of the photorefractive material 33:50:1:16.

ERASABLE/REWRITABLE OPTICAL DATA STORAGE WITH
PHOTOREFRACTIVE POLYMERS

— This invention relates to optical data storage and more particularly to erasable/rewritable three-dimensional optical data storage with photorefractive polymers.

Multi-layered (or three-dimensional) optical memories have increasingly become a field of interest in the development of high-density optical data storage devices. Systems that utilise multiple layer recording can achieve recording densities from 100 to 10,000 times higher than conventional optical data storage devices.

The use of two-photon excitation in three-dimensional (3D) bit optical data storage has grown due to its ability to increase the density in a given material by reducing the volume of the recorded bit. The probability of two-photon excitation is proportional to the squared intensity of the incident light; this effect produces excitation only within a small region of the focus spot. As a result there is less cross talk between neighbouring data layers. Another advantage of two-photon excitation is the reduction of multiple scattering because of the utilisation of an illumination beam of an infrared wavelength, so that more layers can be recorded along the depth of a volume material.

Over the years different materials have been used for 3D bit data storage under two-photon excitation. Two-photon 3D bits recorded in photopolymerizable and photobleaching materials have demonstrated that recording densities could reach terabits per cubic centimeter; unfortunately both materials are not erasable. U.S. Patent No. 5,289,407 assigned to Cornell Research Foundation, Inc. discloses a method of 3D optical data storage in which a beam of coherent light is used to cause two-photon photopolymerization of a specimen gel to produce a bead of polymerised material in the gel which has a different refractive index from the surrounding gel material. However, this change is irreversible, and so the data bits are not erasable.

Photochromic materials that undergo a change in isomer states and photochromic polymers that produce a change in refractive-index upon two-photon excitation are both erasable materials. Another type of material that is of considerable interest is photorefractive material. The photorefractive effect
5 results in a modulation of the refractive-index at the point of focus induced by the spatial distribution of electric charges upon illumination.

It has been discovered that such a change in the refractive index in photorefractive material may be reversed by illuminating the medium again with radiation to produce a uniform redistribution of the electric charges and erase
10 the recorded information. However, this has previously only been achieved in a photorefractive crystals, e.g. lithium niobate (LiNbO_3), which are expensive to manufacture.

It is therefore desirable to provide a method of writing and erasing optical data in relatively inexpensive materials.

15 According to one aspect of the invention, there is provided a method of writing and erasing optical data comprising:

producing a beam of focusable, coherent light;

focussing the beam on a photorefractive polymeric material to cause two-photon excitation of the material at the focal point of the beam thereby
20 modulating the refractive index at the focal point to record data; and

illuminating the material with radiation to erase the recorded data.

According to another aspect of the invention there is provided a method of writing and re-writing optical data in a photorefractive polymeric material comprising:

25 focussing a beam of coherent light on the photorefractive polymeric material to cause two-photon excitation of the material at the focal point of the beam thereby modulating the refractive index at the focal point to write data;

illuminating the material with radiation to erase the recorded data;

focussing another beam of coherent light on the photorefractive material
30 to cause two-photon excitation of the material at the focal point of the beam

thereby modulating the refractive index at the focal point to re-write data in the photorefractive material.

- In the method of the present invention, the two-photon excitation produces a change in the spacial distribution of the electric charges at the focal point, thereby modulating the refractive index of the material at the focal point.

Preferably, the photorefractive polymeric material used in the method is such that illumination with electro-magnetic radiation in the ultraviolet (UV) or visible spectrum produces a uniform redistribution of the spacial distribution of the electric charges forming the data bits to erase the recorded data. The photorefractive polymer is preferably arranged to absorb radiation in only a narrow band in the UV to visible region of the electromagnetic spectrum. Creating a narrow absorption band will decrease the materials susceptibility to deterioration from the reading process or from incidental ultraviolet light (e.g. from sunlight).

- A laser may be used in a pulsed mode or a continuous wave laser may be used to write data by two-photon excitation of a photorefractive material. An ultrashort pulsed laser beam is typically used for two-photon excitation because the cooperative nature of two-photon excitation requires the use of a high peak power laser to produce efficient excitation. However, the use of an ultrashort pulse laser increases the cost of a recording device and makes it difficult to produce a compact system. We have also demonstrated that two-photon excitation under continuous wave (CW) illumination is possible. Although the average power needed for CW excitation is increased by approximately two orders of magnitude compared with ultrashort pulsed illumination, the use of continuous wave illumination can enable a fast, low cost, compact erasable two-photon 3D bit optical data storage system to be achieved.

The photorefractive material preferably includes a chromophore which provides absorption in the UV to visible region. The polymer may also be doped with a photosensitive material which provides absorption in the UV to visible region of the electromagnetic spectrum. In one embodiment, the polymer may comprise poly (N-vinylcarbazole) (PVK). In another preferred

embodiment, the polymer may comprise poly (methyl methacrylate) (PMMA). Each of these polymers may be doped with a photosensitive material, such as 2, 4, 7 - trinitro - 9 -fluorenone (TNF). One preferred chromophore is 2, 5 - dimethyl - 4 - (p - nitrophenylazo) anisole (DMNPAA) which also provides
5 absorption and an electro-optical effect in the UV to visible region. The polymeric material may also include a plasticiser, such as N-ethylcarbazole, (ECZ) to reduce the glass transition temperature of the material.

In the present invention, recorded bits of data may be read by employing a confocal microscope, a differential interference contrast (DIC) microscope
10 and/or a phase microscope utilising a source of coherent light of a wavelength on the edge of or outside the absorption band of the photorefractive polymeric material.

According to a further aspect of the invention there is provided a photorefractive polymeric material for use in a method of erasable optical data
15 storage, the photorefractive polymeric material providing absorption in the UV to visible region of the electromagnetic spectrum, wherein the absorption band of the photorefractive material is such as to enable the recording of bits of data by two photon excitation, the reading of the bits of data by a source of coherent light on the edge of or outside the absorption band, and the erasing of the bits of
20 data by illumination with radiation within the absorption band. The polymeric material preferably comprises a polymer, such as PVK or PMMA. The material may include a chromophore which provides absorption in the UV to visible region of the electromagnetic spectrum. Optionally, the polymer may also be doped with a photosensitive material which provides absorption in the UV to
25 visible region of the electromagnetic spectrum, and a plasticiser may be added to reduce the glass transition temperature of the material.

Preferably, a new photorefractive polymeric material in accordance with the second aspect of the invention includes at least some of the following materials in quantities falling substantially within the following ranges by
30 percentage of the total weight of the photorefractive polymeric material:

25% - 100% of a polymer, such as PVK or PMMA;

0% - 60% of a chromophore, such as DMNPAA;

— 0% - 5% of a photosensitive material, such as TNF; and

0% - 40% of a plasticiser, such as ECZ.

5 Preferred embodiments of the present invention using cheap photorefractive polymers as recording materials for rewritable/erasable 3D bit optical data storage under two-photon excitation to produce a high-density 3D optical data storage system will now be described by way of example only, with reference to the accompanying drawings, in which:-

10 Figure 1 is a graph showing the absorption curve of a photorefractive polymeric material for use in the present invention;

Figure 2 is a schematic diagram of a two-photon excitation microscope used to record data bits in a photorefractive polymer;

Figure 3(a) is a 24 x 24 bit pattern of the letter "C" recorded by two-photon excitation in a photorefractive polymer PVK upon its first reading;

Figure 3(b) is the same region after reading 500 times;

Figure 3(c) is a 24 x 24 bit pattern of the letter "A";

Figure 3(d) is the same region as Figure 3(c) after being exposed to UV illumination showing complete erasure of the recorded information;

20 Figure 4 shows recorded 24 x 24 bit patterns at different depths in the photorefractive polymer PVK using two-photon excitation;

Figure 4(a) shows a first layer including letter "A";

Figure 4(b) shows a second layer including letter "B" and

Figure 4(c) shows a third layer including letter "C";

25 Figure 5 (a) is a bit pattern of the letter "E" recorded by two-photon excitation in another photorefractive polymer (PMMA).

Figure 5 (b) is the same region as Figure 5(a) after being exposed to UV illumination showing erasure of the recorded information;

Figure 5(c) is a bit pattern of the letter "F" written into the same area as
30 Figures 1 and 2;

Figure 6 shows recorded bit patterns at different depths in the photorefractive polymer PMMA using two-photon excitation;

— Figure 6(a) shows a first layer including letter "A";

Figure 6 (b) shows a second layer including letter "B" and

5 Figure 6(c) shows a third layer including letter "C".

One example of a new photorefractive polymeric material that has been used to demonstrate rewritable/erasable 3D bit optical data storage is the polymer poly (*N*-vinylcarbazole (PVK) doped with the photosensitive material 2, 4, 7-trinitro-9-fluorenone (TNF) which provides absorption in the UV to visible region of the spectrum. The photorefractive material also included, as a chromophore, 2, 5-dimethyl-4-(*p*-nitrophenylazo)anisole (DMNPAA) which also provides absorption in the UV to visible region. In this experiment compared with previous experiments the randomly oriented chromophores were not aligned by applying an electric field (poling) during polymerisation and operation. Poling of the material requires the creation of a magnetic field across the surfaces of the polymer. Such a uniform magnetic field is difficult to maintain across the surface of a large polymer sample, increasing the complexity in fabricating the new photorefractive polymer. Finally *N*-ethylcarbazole (ECZ) was added to reduce the glass transition temperature of the material. One preferred concentration of the materials DMNPAA:PVK:ECZ:TNF is 50:33:16:1 by percentage weight of the total weight of the photorefractive material although it will be appreciated that different proportions of the constituent materials may be used within the ranges specified above. Uniform films of thickness 100µm were fabricated by combining all the materials in a teflon cast then polymerising the PVK at a temperature of 90°C over 2 days. The resulting polymer block was cut and polished to produce the sample used in the experiments.

Another example of a new photorefractive polymeric material that has been used to demonstrate rewritable/erasable 3D bit optical data storage is the polymer poly (methyl methacrylate) (PMMA) doped with the photosensitive

material 2, 4, 7-trinitro-9-fluorenone (TNF) which provides absorption in the UV to visible region of the spectrum. The photorefractive material also included, as a chromophore, 2, 5-dimethyl-4-(p-nitrophenylazo)anisole (DMNPAA) which also provides absorption in the UV to visible region. In this experiment the randomly orientated chromophores were not aligned by applying an electric field (poling) during polymerisation and operation. Such a poling electric field is not necessary because the local electric field in the focus produced by a high numerical aperture objective is five orders of magnitude greater than that of the incident beam over the objective aperture. This local electric field is strong enough to induce a detectable electro-optic effect.

Finally N-ethylcarbazole (ECZ) was added to reduce the glass transition temperature of the material. One preferred concentration of the materials DMNPAA:PMMA:ECZ:TNF used was 10:73:16:1 by percentage weight of the total weight of the photorefractive material although it will be appreciated that different proportions of the constituent materials may be used within the ranges specified above. Uniform films of thickness 100µm were fabricated by combining all the materials in a teflon cast then polymerising the PMMA at a temperature of 65°C over 2 days. The resulting polymer block was cut and polished to produce the sample used in the experiments.

Figure 1 illustrates the absorption band of a 100µm thick sample of the new photorefractive polymeric materials based on PVK as detected in an Oriel UV-Vis spectrophotometer using a Xenon arc lamp source. The absorption band of the photorefractive polymeric material based on PMMA is almost identical.

It is seen from Figure 1 that the maximum of the absorption band of the new materials is within 380-600 nm. Therefore a laser beam of an infrared wavelength at 800 nm can be used in the recording process to produce two-photon excitation at 400 nm. The wavelength for recording may fall substantially within the range from about 750 nm to about 1200 nm. Since the absorption band cuts off approximately at a wavelength of 630 nm, a range of wavelengths from about 630 nm to about 1200 nm can be chosen to read out the

recorded photorefractive data bits without suffering from single-or two-photon excitation. Wavelengths above about 750 nm can be used provided the power of the reading beam is sufficiently low as not to cause single or two-photon excitation.

5 Referring to Figure 2, there is illustrated an optical system for two photon recording of bits of data in the photorefractive polymeric materials. The recording system comprises a laser (10), a mechanical shutter (11), linked to a computer (20), lenses (12, 13), a pin hole aperture (14), another aperture (16), and an objective lens (18). For reading with confocal geometry, the system also
10 includes a beam splitter (22), a further lens (24), another pin hole aperture (26) and a detector (28) also linked to the computer (20). A three-dimensional scanning stage (30) is provided for the mounting of the sample of photorefractive material (32). The scanning stage (30) is movable in the x, y and z directions under the control of the computer (20).

15 In the recording process, a Spectra-Physics Tsunami Ti:sapphire laser (10), was focused into the photorefractive polymer sample (32). The laser was used in a pulsed mode to record the bit patterns of Figures 3 and 4 in the PVK photorefractive polymeric material. In mode-locking operation, the laser can produce an ultrashort pulsed beam with a pulse width of 80 fs and an average
20 power of 800 mW. The laser was operated in a continuous wave (CW) mode to record the bit patterns of Figures 5 and 6 in the PMMA photorefractive polymeric material. In each case, the wavelength of the laser was tuned to 800 nm, which approximately corresponds to twice the wavelength of the main absorption band of the sample. From the absorption curve in Figure 1, we can
25 see that there will be no single-photon absorption at a wavelength of 800 nm; only the two-photon absorption can occur at a wavelength of 400 nm. The logic state of the recorded information was controlled by the mechanical shutter (11) linked to the computer (20). The recording material (32) was mounted upon a Melles Griot computer-controlled 3D translation stage (30). For recording, a
30 Zeiss Fluar objective (Figures 3 and 4) and an Olympus UPlanAPO objective

(Figures 5 and 6) (18) with numerical apertures of 0.75 and 0.70 respectively and magnification factors of 20 were used.

— For reading the change in refractive-index caused by the two-photon photorefractive effect an Olympus Fluo View microscope was employed and used in a differential interference contrast (DIC) mode. A He-Ne laser of wavelength 632.8 nm was coupled into the Fluo View for reading the recorded information, as the wavelength of 632.8 nm is on the edge of the absorption band and causes minimal damage to the recorded information (see Fig. 1). To erase the recorded information the region of interest was illuminated with the UV line of a mercury lamp in the Fluo View microscope. In both the reading and erasing an Olympus UPlanAPO objective (18) either with a numerical aperture of 0.7 and a magnification factor of 20 (Figures 3 and 4) or with a numerical aperture of 0.4 and a magnification factor of 10 (Figures 5 and 6) was used.

As a demonstration of the ability to record information as a change in refractive-index using two-photon excitation, Figures 3(a) and 3(b) show the measured change in refractive-index produced at the focus spots. In recording an average power of 5 mW at the focus spot was used to record the information. A pattern (the letter C) consisting of 24 x 24 bits was recorded in the sample. The bit separation was 3.2 μm , and the exposure time for each bit was 25 ms. In the reading process a laser beam of power less than 5mW was scanned across the sample to produce the DIC image. Figure 3(b) shows the deterioration of the recorded information after having been scanned 500 times. The contrast of the recorded bit in Figure 3(b) is 90% of that in Figure 3(a). This feature illustrates that there is a slight erasing of the information due to absorption of the light used for reading. The information recorded in Figure 3(c) used the same power and exposure time as used in Figure 3(a) and Figure 3(b). Figure 3(d) shows the same region as seen in Figure 3(c) after being exposed to the UV illumination for 1-2 seconds. The result shows the complete erasure of the previously recorded information.

Figure 4 demonstrates the ability of this system to record and read changes in refractive-index of multiple layers of information. Three layers of information were recorded with a layer separation of 10 μm . Each layer consists of a pattern of 24 x 24 bits. The first layer, recorded near the surface contains a pattern of the letter "A". The second and third layers consist of the letters "B" and "C" respectively, thus the achieved 3D data density was approximately 10 Gbits/cm³, which is comparable to that previously achieved in photochromic polymers, a photorefractive crystal and photobleaching materials.

Figure 5(a) shows the ability to record information as a change in refractive-index using continuous wave two-photon excitation. In recording an average power of 75 mW at the focus spot was used to record the information. A pattern (the letter E) consisting of 24 x 24 bits was recorded in the sample. The bit separation was 5.6 μm , and the exposure time for each bit was 2 ms. In the reading process a laser beam of power less than 5 mW was scanned across the sample to produce the DIC image. Figure 5(b) shows the same region as seen in Figure 5(a) after being exposed to the UV illumination for 1-2 seconds.

The result shows the complete erasure of the previously recorded information. In Figure 5(c), a new pattern, the letter "F" is written into the same area as used in Figures 5(a) and 5(b). Two artifacts are marked with circles 1 and 2 in Figures 5(a), (b) and (c) showing that the same area was used to erase and rewrite information.

Figure 6 demonstrates the ability of this system to record and read changes in refractive-index of multiple layers of information. Three layers of information were recorded with a layer separation of 25 μm . Each layer consists of a pattern of 24 x 24 bits. The first layer, recorded near the surface contains a pattern of the letter "A". The second and third layers consist of the letters "B" and "C", respectively.

It will be seen from the above that the present invention provides an effective method of recording, reading, erasing and rewriting three dimensional data in relatively inexpensive photorefractive polymeric materials using either pulsed or continuous wave (CW) two-photon excitation to record and re-write

the data, and illuminating with radiation in the UV or visible region of the electromagnetic radiation to erase the recorded data.

— It will also be appreciated that various modifications, alterations and improvements may be made to the preferred embodiment described above without departing from the scope and spirit of the present invention. Such
5 modifications or improvements that are envisaged to increase the storage capacity of the system include the following:

1. The compensation of small amounts of cross talk between the layers (see Figure 4) due to spherical aberration from the refractive-index mismatch between the recording material ($n = 1.75$) and the immersion medium
10 ($n = 1$). The refractive-index mismatch results in an increase in the diffraction spot size at a deep position of a volume recording medium. As a result, a series of axial side peaks occur along the depth of the recording medium, thus resulting in cross talk between neighbouring data layers. It may be possible to
15 overcome this problem thereby increasing the density of data by using a variable tube length method.

2. Instead of the Ti:sapphire laser operated in CW mode, other types of continuous wave (CW) laser beams may be used to produce the two-photon excitation. For example, with the help of a 1.2 W CW laser diode, operated at a
20 near-infrared wavelength, a fast, low cost, compact, erasable two-photon 3D bit optical data storage system can be achieved.

3. Different photorefractive polymers may be used and the chemical properties of the materials may be modified to lead to an increase in the stability of the photorefractive polymer. By tailoring the absorption spectrum we can
25 determine the wavelength of light that will affect the material. Creating a narrow absorption band in the UV or visible region will decrease the materials susceptibility to deterioration due to irradiation from the reading process or from incidental UV light (i.e. sunlight).

4. A method for increasing the density of the two-photon data
30 storage system by utilising a recording method may be based on the polarisation state of the recording beam. This technique allows multiple bits to be recorded

CLAIMS

1. A method of writing and erasing optical data comprising:
 - producing a beam of focusable, coherent light;
 - focussing the beam on a photorefractive polymeric material to cause two-photon excitation of the material at the focal point of the beam thereby modulating the refractive index at the focal point to record data; and
 - illuminating the material with radiation to erase the recorded data.
2. A method of writing and re-writing optical data in a photorefractive polymeric material comprising:
 - focussing a beam of coherent light on the photorefractive polymeric material to cause two-photon excitation of the material at the focal point of the beam thereby modulating the refractive index at the focal point to write data;
 - illuminating the material with radiation to erase the recorded data;
 - focussing another beam of coherent light on the photorefractive polymeric material to cause two-photon excitation of the material at the focal point of the beam thereby modulating the refractive index at the focal point to re-write data in the photorefractive polymeric material.
3. A method according to claim 1 or claim 2 wherein the photorefractive material is illuminated with electro-magnetic radiation having a wavelength in the ultraviolet (UV) or visible spectrum to produce a redistribution of the spacial distribution of the electric charges forming bits of the data to erase the recorded data.
4. A method according to claim 3 wherein the photorefractive polymeric material is such that it absorbs radiation in only a narrow band in the UV to visible region of the electromagnetic spectrum.

5. A method according to claim 3 or claim 4 wherein the maximum of the absorption band of the photorefractive polymeric material falls substantially within the range from about 380nm to about 600 nm.

5 6. A method according to any one of claims 3 to 5 wherein the photorefractive polymeric material is such that it absorbs substantially no radiation above a wavelength of about 630 nm.

10 7. A method according to any one of the preceding claims wherein the data recorded in the photorefractive polymeric material is read by illuminating the photorefractive polymeric material with coherent light of a wavelength falling substantially within the range from about 630 nm to about 1200 nm.

15 8. A method according to any one of the preceding claims wherein the beam of focusable coherent light used to record data in the photorefractive material has a wavelength falling substantially within the range from about 750nm to about 1200 nm to cause two-photon excitation.

20 9. A method according to any one of the preceding claims wherein a pulsed laser beam is used to record data in the photorefractive polymeric material.

10. A method according to any one of claims 1 to 8 wherein a continuous wave laser beam is used to record data in the photorefractive polymeric material.

25 11. A method according to any one of the preceding claims wherein a polarised beam of focusable, coherent light is used to record polarised bits of data in the photorefractive polymeric material.

- 15 -

12. A method according to claim 11 wherein different polarisation states of the recording beam are used to record multiple bits of data at the same position having different polarisation states in the photorefractive polymeric material.
- 5 13. A method according to claim 11 or claim 12 wherein bits of recorded data are read by using a reading beam having an appropriate polarisation state.
14. A method according to any one of claims 11 to 13 wherein individual bits of data are erasable by changing the polarisation state of the individual bits.
- 10 15. A method according to any one of the preceding claims wherein the photorefractive polymeric material includes at least about 25% of a polymer by percentage weight of the total weight of the photorefractive material.
- 15 16. A method according to any one of the preceding claims, wherein the photorefractive polymeric material includes a chromophore which provides absorption in the UV to visible region of the electromagnetic spectrum.
- 20 17. A method according to any one of the preceding claims wherein the photorefractive polymeric material includes a photosensitive material which provides absorption in the UV to visible region of the electromagnetic spectrum.
18. A method according to any one of the preceding claims wherein the photorefractive polymeric material includes a plasticiser to reduce the glass transition temperature of the material.
- 25 19. A method according to any one of the preceding claims wherein the photorefractive material includes at least some of the following materials in quantities falling substantially within the following ranges by percentage of the total weight of the photorefractive material:
- 30

- 16 -

- 25% - 100% of a polymer ;
- 0%-60% of a chromophore;
- 0%-5% of a photosensitive material; and
- 0% - 40% of a plasticiser.

5

20. A method according to claim 15 or claim 19 wherein the polymer comprises poly (*N*-vinylcarbazole) (PVK).

21. A method according to claim 15 or claim 19 wherein the polymer
10 comprises poly (methyl methacrylate) (PMMA).

22. A method according to claim 16 or any one of claims 19 to 21 wherein the chromophore comprises 2, 5- dimethyl - 4 - (p-nitro-phenylazo) anisole (DMNPAA).

15

23. A method according to claim 17 or any one of claims 19 to 22 wherein the photosensitive material comprises 2, 4, 7-trinitro-9-fluorenone (TNF).

24. A method according to any one of claims 19 to 23 wherein the plasticizer
20 comprises *N*-ethylcarbazole (ECZ).

25. A photorefractive polymeric material for use in a method of erasable optical data storage, the photorefractive polymeric material providing absorption in the UV to visible region of the electromagnetic spectrum, wherein
25 the absorption band of the photorefractive material is such as to enable the recording of bits of data by two photon excitation, the reading of the bits of data by a source of coherent light on the edge of or outside the absorption band, and the erasing of the bits of data by illumination with radiation within the absorption band.

30

26. A photorefractive polymeric material according to claim 25 wherein the maximum of the absorption band of the photorefractive material falls substantially within the range from about 380 nm to about 600 nm.

5 27. A photorefractive polymeric material according to claim 25 or claim 26 wherein the upper end of the absorption band of the photorefractive polymeric material is about 630 nm.

28. A photorefractive polymeric material according to any one of claims 25
10 to 27 wherein the material includes at least about 25% of a polymer by percentage weight of the total weight of the photorefractive material.

29. A photorefractive polymeric material according to any one of claims 25
15 to 28 wherein the material includes a chromophore which provides absorption in the UV to visible region of the electromagnetic spectrum.

30. A photorefractive polymeric material according to claim 29 wherein the chromophore is present by an amount falling substantially within the range from about 0.5% to about 60% by percentage weight of the total weight of the
20 material.

31. A photorefractive polymeric material according to any one of claims 25
25 to 30 wherein the material includes a photosensitive material which provides absorption in the UV to visible region of the electromagnetic spectrum.

32. A photorefractive polymeric material according to claim 31 wherein the photosensitive material is present by an amount falling substantially within the range from about 0.5% to about 5% by percentage weight of the total weight of the photosensitive material.

33. A photorefractive polymeric material according to any one of claims 25 to 32 wherein the material includes a plasticiser to reduce the glass transition temperature of the material.
- 5 34. A photorefractive polymeric material according to claim 33 wherein the plasticizer is present by an amount falling substantially within the range from 0% to about 40% by percentage weight of the total weight of the photorefractive polymeric material.
- 10 35. A photorefractive polymeric material for use in a method of optical data storage, wherein the material includes at least some of the following materials in quantities falling substantially within the following ranges by percentage of the total weight of the photorefractive polymeric material;
- 15 25% - 99.5% of a polymer;
0% - 60% of a chromophore;
0% - 5% of a photosensitive material; and
0% - 40% of a plasticiser.
- 20 36. A photorefractive polymeric material according to claim 28 or claim 35 wherein the polymer comprises poly (*N*-vinylcarbazole) (PVK).
37. A photorefractive polymeric material according to claim 28 or claim 35 wherein the polymer comprises poly (methyl methacrylate) (PMMA).
- 25 38. A photorefractive polymeric material according to any one of claims 29, 30 or 35 to 37 wherein the chromophore comprises 2,5-dimethyl-4-(*p*-nitro phenylazo) anisole (DMNPAA).

39. A photorefractive polymeric material according to any one of claims 31, 32, or 35 to 38 wherein the photosensitive material comprises 2, 4, 7-trinitro-9-fluorenone (TNF).

5 40. A photorefractive polymeric material according to any one of claims 33 to 39 wherein the plasticiser comprises *N*-ethylcarbazole (ECZ).

41. A photorefractive polymeric material for use in a method of optical data storage comprising the following materials:

10 poly(*N*-vinylcarbazole) (PVK);
2,5, dimethyl-4-(*p*-nitrophenylazo) anisole (DMNPAA)
2,4,7-trinitro-9-fluorenone (TNF); and
N-ethylcarbazole (ECZ).

15 42. A photorefractive material according to claim 41 wherein the PVK;DMNPAA;TNF and ECZ are present in approximately the following concentrations by percentage weight of the total weight of the photorefractive material 33:50:1:16.

20 43. A photorefractive polymeric material for use in a method of optical data storage comprising the following materials:

poly (methyl methacrylate) (PMMA);
2, 5, dimethyl-4-(*p*-nitrophenylazo) anisole (DMNPAA);
2,4,7-trinitro-9-fluorenone (TNF); and
25 *N*-ethylcarbazole (ECZ).

44. A photorefractive polymeric material according to claim 43 wherein the PMMA: DMNPAA; TNF and ECZ are present in approximately the following concentrations by percentage weight of the total weight of the photorefractive
30 polymeric material 73:10:1:16

AMENDED CLAIMS

[received by the International Bureau on 23 June 2000 (23.06.00);
original claims 1 - 44 replaced by new claims 1 - 45 (8 pages)]

1. A method of writing and erasing optical data comprising:
 - focussing light on a photorefractive polymeric material to cause two-photon excitation of the material at the focal point thereby modulating the refractive index at the focal point to record data; and
 - 5 illuminating the material with radiation to erase the recorded data.
2. A method of writing and re-writing optical data in a photorefractive polymeric material comprising:
 - 10 focussing light on the photorefractive polymeric material to cause two-photon excitation of the material at the focal point of the beam thereby modulating the refractive index at the focal point to write data;
 - illuminating the material with radiation to erase the recorded data;
 - 15 focussing light on the photorefractive polymeric material to cause two-photon excitation of the material at the focal point thereby modulating the refractive index at the focal point to re-write data in the photorefractive polymeric material.
3. A method according to claim 1 or claim 2 wherein the modulation of the refractive index caused by the two-photon excitation is a refractive index inhomogeneity resulting from a non-uniform space-charge distribution within the region of excitation within the photorefractive polymeric material.
4. A method according to any one of claims 1 to 3 wherein the photorefractive material is illuminated with electro-magnetic radiation having a wavelength in the ultraviolet (UV) or visible spectrum to produce a redistribution of the spacial distribution of the electric charges forming bits of the data to erase the recorded data.
- 25

5. A method according to claim 4 wherein the photorefractive polymeric material is such that it absorbs radiation in only a narrow band in the UV to visible region of the electromagnetic spectrum.

5 6. A method according to claim 4 or claim 5 wherein the maximum of the absorption band of the photorefractive polymeric material falls substantially within the range from about 380nm to about 600 nm.

7. A method according to any one of claims 4 to 6 wherein the
10 photorefractive polymeric material is such that it absorbs substantially no radiation above a wavelength of about 630 nm.

8. A method according to any one of the preceding claims wherein the data recorded in the photorefractive polymeric material is read by illuminating the
15 photorefractive polymeric material with coherent light of a wavelength falling substantially within the range from about 630 nm to about 1200 nm.

9. A method according to any one of the preceding claims wherein the light used to record data in the photorefractive material has a wavelength falling
20 substantially within the range from about 750nm to about 1200 nm to cause two-photon excitation.

10. A method according to any one of the preceding claims wherein a pulsed laser beam is used to record data in the photorefractive polymeric material.

25

11. A method according to any one of claims 1 to 9 wherein a continuous wave laser beam is used to record data in the photorefractive polymeric material.

12. A method according to any one of the preceding claims wherein polarised coherent light is used to record polarised bits of data in the photorefractive polymeric material.

5 13. A method according to claim 12 wherein different polarisation states of the recording beam are used to record multiple bits of data at the same position having different polarisation states in the photorefractive polymeric material.

10 14. A method according to claim 12 or claim 13 wherein bits of recorded data are read by using a reading beam having an appropriate polarisation state.

15 15. A method according to any one of claims 12 to 14 wherein individual bits of data are erasable by changing the polarisation state of the individual bits.

16 16. A method according to any one of the preceding claims wherein the photorefractive polymeric material includes at least about 25% of a polymer by percentage weight of the total weight of the photorefractive material.

20 17. A method according to any one of the preceding claims, wherein the photorefractive polymeric material includes a chromophore which provides absorption in the UV to visible region of the electromagnetic spectrum.

25 18. A method according to any one of the preceding claims wherein the photorefractive polymeric material includes a photosensitive material which provides absorption in the UV to visible region of the electromagnetic spectrum.

19. A method according to any one of the preceding claims wherein the photorefractive polymeric material includes a plasticiser to reduce the glass transition temperature of the material.

20. A method according to any one of the preceding claims wherein the photorefractive material includes at least some of the following materials in quantities falling substantially within the following ranges by percentage of the total weight of the photorefractive material:

5

- 25% - 100% of a polymer ;
- 0%-60% of a chromophore;
- 0%-5% of a photosensitive material; and
- 0% - 40% of a plasticiser.

10

21. A method according to claim 16 or claim 20 wherein the polymer comprises poly (*N*-vinylcarbazole) (PVK).

15

22. A method according to claim 16 or claim 20 wherein the polymer comprises poly (methyl methacrylate) (PMMA).

20

23. A method according to claim 17 or any one of claims 20 to 22 wherein the chromophore comprises 2, 5- dimethyl - 4 - (p-nitro-phenylazo) anisole (DMNPAA).

24. A method according to claim 18 or any one of claims 20 to 22 wherein the photosensitive material comprises 2, 4, 7-trinitro-9-fluorenone (TNF). -

25

25. A method according to any one of claims 20 to 24 wherein the plasticizer comprises *N*-ethylcarbazole (ECZ).

30

26. A photorefractive polymeric material for use in a method of erasable optical data storage, the photorefractive polymeric material providing absorption in the UV to visible region of the electromagnetic spectrum, wherein the absorption band of the photorefractive material is such as to enable the recording of bits of data by two photon excitation, the reading of the bits of data

by a source of coherent light on the edge of or outside the absorption band, and the erasing of the bits of data by illumination with radiation within the absorption band.

- 5 27. A photorefractive polymeric material according to claim 26 wherein the maximum of the absorption band of the photorefractive material falls substantially within the range from about 380 nm to about 600 nm.

- 10 28. A photorefractive polymeric material according to claim 26 or claim 27 wherein the upper end of the absorption band of the photorefractive polymeric material is about 630 nm.

- 15 29. A photorefractive polymeric material according to any one of claims 26 to 28 wherein the material includes at least about 25% of a polymer by percentage weight of the total weight of the photorefractive material.

- 20 30. A photorefractive polymeric material according to any one of claims 26 to 29 wherein the material includes a chromophore which provides absorption in the UV to visible region of the electromagnetic spectrum.

- 25 31. A photorefractive polymeric material according to claim 30 wherein the chromophore is present by an amount falling substantially within the range from about 0.5% to about 60% by percentage weight of the total weight of the material.

32. A photorefractive polymeric material according to any one of claims 26 to 31 wherein the material includes a photosensitive material which provides absorption in the UV to visible region of the electromagnetic spectrum.

- 30 33. A photorefractive polymeric material according to claim 32 wherein the photosensitive material is present by an amount falling substantially within the

range from about 0.5% to about 5% by percentage weight of the total weight of the photosensitive material.

34. A photorefractive polymeric material according to any one of claims 26 to 33 wherein the material includes a plasticiser to reduce the glass transition temperature of the material.

35. A photorefractive polymeric material according to claim 33 wherein the plasticizer is present by an amount falling substantially within the range from 0% to about 40% by percentage weight of the total weight of the photorefractive polymeric material.

36. A photorefractive polymeric material for use in a method of erasable/rewritable optical data storage, wherein the material includes at least some of the following materials in quantities falling substantially within the following ranges by percentage of the total weight of the photorefractive polymeric material;

25% - 100% of a polymer;
0% - 60% of a chromophore;
0% - 5% of a photosensitive material; and
0% - 40% of a plasticiser.

37. A photorefractive polymeric material according to claim 29 or claim 36 wherein the polymer comprises poly (*N*-vinylcarbazole) (PVK).

38. A photorefractive polymeric material according to claim 29 or claim 36 wherein the polymer comprises poly (methyl methacrylate) (PMMA).

39. A photorefractive polymeric material according to any one of claims 30, 31 or 36 to 38 wherein the chromophore comprises 2,5-dimethyl-4-(p-nitro phenylazo) anisole (DMNPAA).

5 40. A photorefractive polymeric material according to any one of claims 32, 34 or 36 to 39 wherein the photosensitive material comprises 2, 4, 7-trinitro-9-fluorenone (TNF).

41. A photorefractive polymeric material according to any one of claims 34
10 to 40 wherein the plasticiser comprises *N*-ethylcarbazole (ECZ).

42. A photorefractive polymeric material for use in a method of erasable/rewritable optical data storage comprising the following materials:

15 poly(*N*-vinylcarbazole) (PVK);
2,5, dimethyl-4-(p-nitrophenylazo) anisole (DMNPAA)
2,4,7-trinitro-9-fluorenone (TNF); and
N-ethylcarbazole (ECZ).

43. A photorefractive material according to claim 42 wherein the
20 PVK;DMNPAA;TNF and ECZ are present in approximately the following concentrations by percentage weight of the total weight of the photorefractive material 33:50:1:16.

44. A photorefractive polymeric material for use in a method of optical data
25 storage comprising the following materials:

poly (methyl methacrylate) (PMMA);
2, 5, dimethyl-4-(p-nitrophenylazo) anisole (DMNPAA);
2,4,7-trinitro-9-fluorenone (TNF); and
N-ethylcarbazole (ECZ).

45. A photorefractive polymeric material according to claim 44 wherein the PMMA: DMNPAA; TNF and ECZ are present in approximately the following concentrations by percentage weight of the total weight of the photorefractive polymeric material 73:10:1:16.




Figure 1.






Figure 2.




(a)



(b)



(c)




(d)


Figure 3.

WO 00/49465

PCT/AU00/00117



(a)



(b)




(c)


Figure 4.

WO 00/49465


PCT/AU00/00117



(a)




(b)




(c)


Figure 5.



(a)



(b)



(c)

Figure 6.

COMBINED DECLARATION AND
POWER OF ATTORNEY

IN NATIONAL STAGE OF PCT APPLICATION

Attorney Docket No.

V20.12-0001

SPECIFICATION AND INVENTORSHIP IDENTIFICATION

As a below named inventor, I declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and joint inventor of the subject matter which is claimed, and for which a patent is sought, on the invention entitled ERASABLE/REWRITABLE OPTICAL DATA STORAGE WITH PHOTOREFRACTIVE POLYMERS the specification of which,

(check one) ☐ is attached hereto.

☒ was filed on ~~XXXXXXX Serial No. XXXXX~~ August 17, 2001 as Serial No. 09/913,673 and was amended on .
☒ was described and claimed in PCT International Application No. PCT/AU00/00117 filed on 16 February 2000 and as amended under PCT Article 19 on 23 June 2000.

ACKNOWLEDGEMENT OF REVIEW OF PAPERS AND DUTY OF CANDOR

I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above. I acknowledge the duty to disclose information which is known to me to be material to the patentability of this application in accordance with Title 37, Code of Federal Regulations, § 1.56.

PRIORITY CLAIM (35 USC § 119)

I claim foreign priority benefits under Title 35, United States Code, § 119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

Prior Foreign Application(s)

Number	Country	Day/Month/Year Filed	Priority Claimed
<u>PCT/AU00/00117</u>	<u>PCT</u>	<u>16 February 2000</u>	Yes <input checked="" type="checkbox"/> No <input type="checkbox"/>
<u>PP8738</u>	<u>Australia</u>	<u>17 February 1999</u>	Yes <input checked="" type="checkbox"/> No <input type="checkbox"/>
<u>PQ3413</u>	<u>Australia</u>	<u>14 October 1999</u>	Yes <input checked="" type="checkbox"/> No <input type="checkbox"/>

PRIORITY CLAIM (35 USC § 120)

I claim the benefit under Title 35, United States Code, § 120 of any United States application(s) listed below. Insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35 United States Code § 112, I acknowledge the duty to disclose to the Patent Office all information known to me to be material to patentability as defined in Title 37 Code of Federal Regulations § 1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application:

Appln. Ser. No.	U.S. Serial No. (if any under PCT)	Filing Date	Status
_____	_____	_____	_____
_____	_____	_____	_____

DECLARATION

I declare that all statements made herein that are of my own knowledge are true and that all statements that are made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

POWER OF ATTORNEY

I appoint the following attorneys and agents to prosecute the patent application identified above and to transact all business in the Patent and Trademark Office connected therewith, including full power of association, substitution and revocation: Judson K. Champlin, Reg. No. 34,797; Joseph R. Kelly, Reg. No. 34,847; Nickolas E. Westman, Reg. No. 20,147; Steven M. Koehler, Reg. No. 36,188; David D. Brush, Reg. No. 34,557; John D. Veldhuis-Kroeze, Reg. No. 38,354; Deirdre Megley Kvale, Reg. No. 35,612; Theodore M. Magee, Reg. No. 39,758; Peter S. Dardi, Reg. No. 39,650; Christopher R. Christenson, Reg. No. 42,413; John A. Wiberg, Reg. No. 44,401; Brian D. Kaul, Reg. No. 41,885; and Robert M. Angus, Reg. No. 24,383.

I ratify all prior actions taken by Westman, Champlin & Kelly, P.A. or the attorneys and agents mentioned above in connection with the prosecution of the above-mentioned patent application.

DESIGNATION OF CORRESPONDENCE ADDRESS

Please address all correspondence and telephone calls to Nickolas E. Westman in care of:

WESTMAN, CHAMPLIN & KELLY, P.A.
Suite 1600 - International Centre
900 Second Avenue South
Minneapolis, Minnesota 55402-3319
 Phone: (612) 334-3222
 Fax: (612) 334-3312

Inventor: 
 (Signature)

Date: Sept. 18, 2001

Inventor: Min Gu
 (Printed Name)


Residence: Victoria, Australia

Citizenship: Australia

AUX

P.O. Address: 4 Maverick Close, Doncaster, Victoria 3108 Australia

200

Inventor: 
(Signature)

Date: 18/09/01

Inventor: Daniel J. Day
(Printed Name)

Residence: Victoria, Australia

Citizenship: Australia

AUX

P.O. Address: 7/100 Curzon Street, North Melbourne, Victoria, Australia

05043673 702501

Inventor: _____
(Signature)

Date: _____

Inventor: Andrew J. Smallridge
(Printed Name)

Residence: Victoria, Australia

Citizenship: Australia

AUX

P.O. Address: 3 Melosa Avenue, East Brighton, Victoria 3187 Australia

**COMBINED DECLARATION AND
POWER OF ATTORNEY
IN NATIONAL STAGE OF PCT APPLICATION**

Attorney Docket No.

V20.12-0001

SPECIFICATION AND INVENTORSHIP IDENTIFICATION

As a below named inventor, I declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and joint inventor of the subject matter which is claimed, and for which a patent is sought, on the invention entitled ERASABLE/REWRITABLE OPTICAL DATA STORAGE WITH PHOTOREFRACTIVE POLYMERS the specification of which,

(check one) ☐ is attached hereto.
☐ was filed on as Appln. Serial No. .
☐ and was amended on .
☒ was described and claimed in PCT International Application No. PCT/AU00/00117 filed on 16 February 2000 and as amended under PCT Article 19 on 23 June 2000.

ACKNOWLEDGEMENT OF REVIEW OF PAPERS AND DUTY OF CANDOR

I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above. I acknowledge the duty to disclose information which is known to me to be material to the patentability of this application in accordance with Title 37, Code of Federal Regulations, § 1.56.

PRIORITY CLAIM (35 USC § 119)

I claim foreign priority benefits under Title 35, United States Code, § 119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

Prior Foreign Application(s)

Number	Country	Day/Month/Year Filed	Priority Claimed	
<u>PCT/AU00/00117</u>	<u>PCT</u>	<u>16 February 2000</u>	Yes <u>X</u>	No <u> </u>
<u>PP8738</u>	<u>Australia</u>	<u>17 February 1999</u>	Yes <u>X</u>	No <u> </u>
<u>PQ3413</u>	<u>Australia</u>	<u>14 October 1999</u>	Yes <u>X</u>	No <u> </u>

PRIORITY CLAIM (35 USC § 120)

I claim the benefit under Title 35, United States Code, § 120 of any United States application(s) listed below. Insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35 United States Code § 112, I acknowledge the duty to disclose to the Patent Office all information known to me to be material to patentability as defined in Title 37 Code of Federal Regulations § 1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application:

Appln. Ser. No.	U.S. Serial No.	Filing Date	Status
	(if any under PCT)		
_____	_____	_____	_____
_____	_____	_____	_____

DECLARATION

I declare that all statements made herein that are of my own knowledge are true and that all statements that are made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

POWER OF ATTORNEY

I appoint the following attorneys and agents to prosecute the patent application identified above and to transact all business in the Patent and Trademark Office connected therewith, including full power of association, substitution and revocation: Judson K. Champlin, Reg. No. 34,797; Joseph R. Kelly, Reg. No. 34,847; Nickolas E. Westman, Reg. No. 20,147; Steven M. Koehler, Reg. No. 36,188; David D. Brush, Reg. No. 34,557; John D. Veldhuis-Kroeze, Reg. No. 38,354; Deirdre Megley Kvale, Reg. No. 35,612; Theodore M. Magee, Reg. No. 39,758; Peter S. Dardi, Reg. No. 39,650; Christopher R. Christenson, Reg. No. 42,413; John A. Wiberg, Reg. No. 44,401; Brian D. Kaul, Reg. No. 41,885; and Robert M. Angus, Reg. No. 24,383.

I ratify all prior actions taken by Westman, Champlin & Kelly, P.A. or the attorneys and agents mentioned above in connection with the prosecution of the above-mentioned patent application.

DESIGNATION OF CORRESPONDENCE ADDRESS

Please address all correspondence and telephone calls to Nickolas E. Westman in care of:

WESTMAN, CHAMPLIN & KELLY, P.A.
Suite 1600 - International Centre
900 Second Avenue South
Minneapolis, Minnesota 55402-3319
Phone: (612) 334-3222
Fax: (612) 334-3312

Inventor: _____
(Signature)

Date: _____

Inventor: Min Gu
(Printed Name)

Residence: Victoria, Australia

Citizenship: Australia

P.O. Address: 4 Maverick Close, Doncaster, Victoria 3108 Australia

Inventor: _____
(Signature)

Date: _____

Inventor: Daniel J. Day
(Printed Name)

Residence: Victoria, Australia

Citizenship: Australia

P.O. Address: 7/100 Curzon Street, North Melbourne, Victoria, Australia

Inventor: _____
(Signature)

Date: _____


Inventor: Andrew J. Smallridge
(Printed Name)

Residence: Victoria, Australia

Citizenship: Australia

P.O. Address: 3 Melosa Avenue, East Brighton, Victoria 3187 Australia

United States Patent & Trademark Office
Office of Initial Patent Examination -- Scanning Division



Application deficiencies found during scanning:

☐ Page(s) _____ of _____ were not present
for scanning. (Document title)

☐ Page(s) _____ of _____ were not
present
for scanning. (Document title)

X Scanned copy is best available. drawing very dark